

# NARVA8 B (ESR)

Forged Tool Steel

### Chemical composition

	С	Cr	Мо	W	Co	٧
NARVA8 B	0,9	8.0	1,5	-	-	2,5
NARVA8 A	0,6	8.0	1,3	1,1	_	_

### **Properties**

	Hardness HRC	Young's modulus GPa	
NARVA8 B	≤ 63	222	
NARVA8 A	≤ 61	210	

## Comparative properties

	Wear resistance	Toughness	Grindability
NARVA8 B			
NARVA8 A			
NARVA12 A			

### Description

Medium alloyed tool steel manufactured according to Union Electric Åkers specification.

NARVA8 B is normally through hardened but can for some special applications be induction hardened.

NARVA8 B is also available further refined by ESR (Electro Slag Remelting).

# **Applications**

1<sup>st</sup> Intermediate rolls in 20-high mills for cold rolling of ferrous and non ferrous products.

2<sup>nd</sup> Intermediate rolls in 20-high mills for cold rolling of ferrous and non ferrous products.

Work rolls in 20-high mills for cold rolling of ferrous and non ferrous products.

Work rolls in highly stressed 2-high and 4-high narrow strip mills for cold rolling of ferrous and non ferrous products.

# Features & Benefits

- A high vanadium content provides an excellent compromise between high wear resistance and toughness.
- Suitable for severe rolling conditions.
  - The rolling of silicon steels.
  - The rolling of low carbon steels.

Union Electric Åkers www.uniones.com